

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 0 754 017 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
**19.06.2002 Bulletin 2002/25**

(51) Int Cl.<sup>7</sup>: **A61F 2/06, A61L 31/00,  
A61L 27/00**

(21) Application number: **95917692.6**

(86) International application number:  
**PCT/US95/05147**

(22) Date of filing: **26.04.1995**

(87) International publication number:  
**WO 95/29647 (09.11.1995 Gazette 1995/48)**

(54) **STENT WITH COLLAGEN**

STENT MIT KOLLAGEN

EXTENSEUR AVEC COLLAGENE

(84) Designated Contracting States:  
**AT BE CH DE DK ES FR GB GR IE IT LI LU MC NL  
PT SE**

(30) Priority: **29.04.1994 US 235300  
06.12.1994 US 350223**

(43) Date of publication of application:  
**22.01.1997 Bulletin 1997/04**

(60) Divisional application:  
**01125379.6**

(73) Proprietor: **Scimed Life Systems, Inc.  
Maple Grove, Minnesota 55311-1566 (US)**

(72) Inventors:  
• **BUIRGE, Andrew, W.**  
**Minneapolis, MN 55406 (US)**  
• **BUSCEMI, Paul, J.**  
**Long Lake, MN 55356 (US)**

• **BURMEISTER, Paul, H.**  
**Maple Grove, MN 55311 (US)**

(74) Representative: **Maiwald, Walter, Dr. Dipl.-Chem.**  
**Maiwald Patentanwalts GmbH**  
**Elisenhof**  
**Elisenstrasse 3**  
**80335 München (DE)**

(56) References cited:  
**EP-A- 0 150 608 EP-A- 0 461 791**  
**EP-A- 0 493 788 WO-A-82/01647**  
**WO-A-93/06792 WO-A-93/20757**  
**GB-A- 2 187 463 US-A- 3 758 396**  
**US-A- 3 892 648 US-A- 4 378 017**  
**US-A- 4 591 456 US-A- 5 100 429**  
**US-A- 5 131 907 US-A- 5 131 908**  
**US-A- 5 147 370**

• **MARCEL E. NIMNI: "Collagen", 1988, CRC  
PRESS, BOCA RATON, FLORIDA**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 0 754 017 B1**

Am

## Description

### Background of the Invention

[0001] This invention relates to vascular prostheses of improved biocompatibility and more specifically to stents in combination with a collagen material. Such a combination provides an endovascular stent which protects the vascular wall and forms a non-thrombogenic cushion for the stent in the vascular lumen.

[0002] It also relates to stents in combination with a collagen liner material. Such a combination provides an endoluminal stent which engages the luminal wall and in the case of vascular applications, forms a non-thrombogenic surface as well as providing for the growth of endothelial cells, as well as a reservoir or point of attachment for therapeutic agents in any application.

[0003] It also relates to combinations of both of the foregoing arrangements.

[0004] Broadly, it relates to stents associated with an outer covering of collagen material and/or a luminal liner of same.

[0005] Stents are generally tubular in configuration, are open ended, and are radially expandable between a generally unexpanded insertion diameter and an expanded implantation diameter which is greater than the unexpanded insertion diameter. Such intravascular implants are used for maintaining vascular patency in humans and animals.

[0006] Stents are typically placed or implanted by a mechanical transluminal procedure. One common procedure for implanting a stent is to first open the region of the vessels with a balloon catheter and then place the stent in a position that bridges the treated portion of the vessel by means of a placement catheter.

[0007] Prior art patents refer to the construction and design of stents as well as apparatus for positioning stents within a vessel. In general, for example, such patents disclose a technique for positioning an elongated cylindrical stent at a region of an aneurysm, stenosis or the like. The stent expands as necessary to an implanted configuration after insertion with the aid of a catheter.

[0008] Specifically, U.S. patent 4,733,665 to Palmaz which issued March 29, 1988, discloses a number of stent configurations for implantation with the aid of a catheter. The catheter includes means for mounting and retaining the stent, preferably on an inflatable portion of the catheter. The stent is implanted by positioning it within the blood vessel and monitoring its position on a viewing monitor. Once the stent is properly positioned, the catheter is expanded and the stent separated from the catheter body. The catheter can then be withdrawn from the subject, leaving the stent in place within the blood vessel. U.S. patent 4,950,227 to Savin et al., which issued on August 21, 1990 is similar.

[0009] Another similar U.S. patent 5,019,090 discloses a generally cylindrical stent and a technique for implanting it using a deflated balloon catheter to position

the stent within a vessel. Once the stent is properly positioned the balloon is inflated to press the stent against the inner wall linings of the vessel. The balloon is then deflated and withdrawn from the vessel, leaving the stent in place.

[0010] A patent to Dotter, U.S. Patent 4,503,569 which issued March 12, 1985 discloses a spring stent which expands to an implanted configuration with a change in temperature. The spring stent is implanted in a coiled orientation and heated to cause the spring to expand due to the characteristics of the shape memory alloy from which the stent is made. Similarly, U.S. patent 4,512,338 to Balko et al., which issued April 23, 1985, discloses a shape memory alloy stent and method for its delivery and use other kinds of self-expanding stents are known in the art.

[0011] The delivery and expansion of the stent of the invention is the same as that already known in the art and practiced with the stent of Figures 1 and 6. U.S. patents 5,195,984 to Schatz, issued March 23, 1993, describes a typical balloon expansion procedure for an expandable stent. That patent describes a catheter having an expandable inflatable portion associated therewith. In a conventional manner, the catheter and stent are delivered to a desired location within a body passageway at which it is desired to expand the stent for implantation. Fluoroscopy, and or other conventional techniques may be utilized to insure that the catheter and graft are delivered to the desired location. The stent is then controllably expanded and deformed by controllably expanding the expandable inflatable portion of catheter, typically a balloon. As a result the stent is deformed radially outwardly into contact with the walls of the body passageway. In this regard, the expandable inflatable portion of the catheter may be a conventional angioplasty balloon as is already known in the art. After the desired expansion and deformation of the stent has been accomplished, the angioplasty balloon may be deflated and the catheter removed in a conventional manner from the passageway.

[0012] Also, this invention is useful in self-expanding stents such as those disclosed in U.S. patents 4,732,152 and 4,848,343.

[0013] A vascular prosthesis comprised of a support framework and a collagen material overlying at least a surface portion thereof, the support framework comprising an expandable stent having a collapsed cylindrical position and an expanded cylindrical position is shown in EP-A-0 461 791.

### Summary of the Invention

[0014] The present invention is directed to a vascular prosthesis as recited in claim 1.

[0015] In one preferred form a metal or other stent for vascular implantation is provided with a covering sleeve of collagen material. The stent may be of the variable diameter type, the sleeve may be stretched into place

or otherwise positioned between the stent and the vascular wall when the stent is seated or deployed. A drug or other agent such as heparin or the like may be included in the collagen for release after stent deployment.

**[0016]** In another preferred form a metal or other stent for vascular implantation is provided with a luminal liner of collagen material. A drug or other agent such as heparin or the like may be included in the collagen as a surface treatment or for release after stent deployment.

**[0017]** In yet another preferred form, a stent is provided with both an inner collagen liner and outer collagen coating.

#### Brief Description of the Figures

**[0018]** Figure 1 shows a stent and covering sleeve combination being formed according to the invention.

**[0019]** Figure 2 is a fragmentary showing of collagen with a fabric support.

**[0020]** Figure 3 shows an example of another self-expanding stent configuration useful in the invention.

**[0021]** Figure 4 shows another stent configuration useful in the invention.

**[0022]** Figures 5 and 6 show a flexible stent configuration which may incorporate a covering sleeve according to the invention.

**[0023]** Figure 7 is similar to Figure 1, showing a combination being formed including an internal liner and an external sleeve for a stent, according to the invention.

**[0024]** Figure 8 is a showing of an alternate mode of manufacture of the invention by molding the collagen to the stent.

**[0025]** Figure 9 shows a stent and an internal liner sleeve combination being formed according to the invention.

**[0026]** Figures 10 shows a bilayer collagen material in schematic and fragmentary form.

**[0027]** Figures 11, 12, and 13 are schematic longitudinal cross-sectional views of a stent carrying inner and outer layers of collagen material.

**[0028]** Figure 14 is a showing of an alternate stent/liner arrangement.

**[0029]** Figure 15 shows an optional technique for forming the stent/liner arrangement by molding.

**[0030]** Figures 16, 17, and 18, schematically show the stretch of a collagen stent being oriented on a bias with respect to a stent.

**[0031]** Figures 19 and 20 show a coated stent, Figure 20 being a cross-sectional view of Figure 19.

#### Detailed Description of the Preferred Embodiment

**[0032]** Referring now to Figure 1, a tubular metal stent generally indicated at 10 is shown being combined with a covering sleeve of collagen material generally indicated at 12 to provide the combination stent/sleeve generally indicated at 14 for the purpose of vascular implantation.

**[0033]** Stent 10 is of the type, typically of a metal such as for example stainless steel, nitinol, superelastic alloys and other metals or a suitable polymeric plastic and may be of a fixed diameter or of a variable diameter, the latter being more preferred and well known in the art. The variable diameter type are usually either balloon expandable or self-expanding, both of which are also known in the art. Examples of the former type are shown in U.S. Patent 4,733,665, U.S. Patent 4,739,762 and U.S. Patent 4,776,337. The latter type is preferred for the purposes of this invention at present, i.e., self-expanding, particularly those made of Nitinol an example of which is discussed in the U.S. Patents 4,503,569 and 4,512,338. Also, for example, useful stents are shown in co-pending application Serial Number 08/246,320 filed May 19, 1994 entitled "Improved Tissue Supporting Devices".

**[0034]** In any event, generally a stent provides a supporting framework structure which may take many forms. Typically stents are open or perforate and may be comprised of a network of struts or wire-like structure. Stent 10 is comprised of struts.

**[0035]** Collagen sleeve 12 shown in Figure 1 may be comprised of collagen per se or it 12a may be carried on a support 12b as shown in Figure 2, support 12b being of DACRON® fabric or the like as is known and disclosed for example in U.S. Patents 5,256,418, 5,201,764 and 5,197,977. The Support 12b may be a fabric, woven or braided, and may also be of polyester, polyethylene, polyurethane or PTFE. The term "collagen material" is used herein to refer to both supported and unsupported collagen for the sleeve element of this invention.

**[0036]** The preferred collagen at present appears, for the purposes of this invention, to be that composed of bovine or porcine Type I or Type IV collagen and combinations thereof in bilayer sheet-like form. The collagen may also be made of Type III or combinations of any of the various types. U.S. Patents 4,837,379; 4,902,508; 4,950,483; 4,956,178; 5,106,949; 5,110,064; 5,256,418; 5,275,826; 5,281,422 and 5,024,841 relate to collagen compositions and production useful in this invention. Collagen can be extracted from various structural tissues as is known in the art and reformed into sheets or tubes and dried onto a stent. Generally, the thickness of these sheets or tubes will range from about 5 to 200 microns. One preferred collagen at present is that disclosed in U.S. Patent 4,902,508 coated as described in U.S. Patent 5,275,826 to provide bilayer SIS as described further hereinbelow. Another preferred collagen is that described as a "collagen construct" in United States Patent 5,256,418, particularly in which the permeable substrate is also collagen.

**[0037]** Cells of the blood vessel wall synthesize and secrete several kinds of macromolecules forming extracellular matrix. The components of this matrix comprise several large proteins that may be synthetically constructed to form films, tubes or multilayer sheets or other

constructs. Among these biological components are collagens of several types, elastin, glycosaminoglycans (GAGS), fibronectin and laminin. Collagens are three chain glycoproteins with molecular weights of about 300,000. Elastin is an insoluble nonpolar amine acid rich crosslinked protein. The GAGs are linear chain polysaccharides with various negative charges with various molecular weights ranging from thousands to millions. Included in the GAGs are heparin and heparin sulfate, dermatin sulfate and chondroitin sulfate. Fibronectin is a 440,000 MW 2-chain adhesive glycoprotein that acts as a substrate for many cell types and in cell-cell interactions. Laminin is a 2 chain glycoprotein of MW about 850,000 and acts as a basement membrane structure for cellular-molecular interactions. Each of these macromolecules may be combined in a multitude of combinations to form composites. These are all natural materials that serve specific functions and are exposed to blood under normal repair conditions. It is therefore expected that, if a covering sleeve for a stent were made of these macromolecules and used in the course of intervention, repair of a blood vessel would proceed more naturally than if a similar device were constructed of synthetic polymers such as polyethylene, polyterephthalate or polyurethanes. Such materials are also referred to herein generally as "collagen". The term "collagen" herein thus refers to not only the specific class of macromolecules known as collagen but those natural materials that normally or naturally form membranes with collagen such as laminin, keratin, glycosaminoglycans, proteoglycans, pure carbohydrates, fibrin, fibronectin, hyaluronic acid or the like, and other natural materials that come into contact with collagen that can be made into film, including albumin, globulins, and other blood borne proteins. Tubular films made from any combination of the above materials will provide substantially the same purpose as that of pure collagen.

**[0038]** The interaction of blood with the differing membrane components described above determines subsequent reactions in the repair of blood vasculature. The initial thrombus formation adhesion and activation of platelets and the initial events related to intimal hyperplasia such as damage to the internal elastic lamina are among those events. These events are natural components of the repair process. Normally these events do not hamper the flow conditions of blood except in the cases of severe trauma. Microthrombi constantly form and disperse on blood vessel surfaces so it would be advantageous to form stent or graft coverings of materials that are accustomed to having thrombus form so that subsequent lysis reactions of those thrombi can proceed in a natural and unobtrusive manner. A sleeve or liner made of these macromolecular components forming a protective layer will prove advantageous when used with stents. Metal or polymeric stents which will provide mechanical stability to the arterial wall to hold up dissected tissue may also be used to hold a sleeve comprised of collagen.

**[0039]** Nevertheless, because anything not formed in the body as a natural component may elicit extreme and unexpected responses as blood vessel closure due to thrombus formation or spasm and because damage to blood vessels by the act of insertion itself of a device may be extreme and unduly injurious to the blood vessel surface, it is prudent to protect against such events. The materials described above are capable of being manipulated to become hydrophilic or hydrophobic with thicknesses ranging from about 5 to several hundred microns. They can be made water soluble, insoluble and with various porosities. They can also be constructed to have regions of various hydrophilicity and porosity. Porosity control is well known.

**[0040]** As such, stent sleeves or liners constructed of these materials can be used for reservoirs for pharmaceutical agents and the like. Hydrophilic drugs such as heparin or hirudin to protect against coagulation or hydrophobic drugs such as prostaglandins or aspirin and vitamin E may be used to protect against platelet activation. Vitamin E and other anti oxidants such as sodium ascorbate, phenidies, carbazoles, and tocotrienols may be used to protect against oxidation. Most preferably, the collagen material will include a quantity of drug material such as heparin which may be incorporated into the collagen in known manner for release after placement of the stent. Generally, the drug materials may include the known antithrombic agents, antibacterial and/or antimicrobial agents, antifungal agents and the like.

**[0041]** During the formation process of the sleeve or sheet, various components may be added to the solution prior to drying or may be added separately after formation of the device. Heparin may be directly added to the forming solution as may be aspirin. Benzalkonium heparin, a modified form of heparin which makes it more hydrophobic may be used to coat the formed device or film from a solution of alcohol. Prostaglandins PGI<sub>2</sub> or PGE<sub>2</sub> may be added from a solution of propanol or propanol/methylene chloride onto a collagen sleeve formed from an aqueous base. Vitamin E may be added from even less polar solutions as chloroform. RGD peptide, thrombomodulin, TPA (Tissue Plasminogen Activator) and Urokinase are examples of bioactive proteins which may be added. Gene therapy agents such as antiplatelet and antibody fragments, for example GB2B3A may be included. Other agents could be similarly added. The term "agents" is used herein to include all such additives.

**[0042]** Vitamin E is a known antioxidant. It is used in polymers and as a drug. It could also be used in biodegradable stents for multiple purposes. In those polymeric type stents that require some form of energy as heat or light to be delivered it could serve to protect the polymers therein against unwanted oxidation caused by the energy source. Also, because tissue damage is caused by oxidation originating from cellular components as macrophages and neutrophils, Vitamin E could serve to protect the tissue as it leached from implanted

devices. It could also serve to protect the polymer during extrusion or heat forming as pressing films. It could also serve to plasticize the material in place of using other non FDA approved materials. It is therefore contemplated that Vitamin E may also be used in combination with the stent or collagen material or the like in this invention for several purposes.

**[0043]** A primary result of the use of a collagen sleeve made of natural components is that cellular regrowth of endothelium will take place onto a natural substrate that is essentially undamaged and uniform and protects against tissue flaps and exposure of necrotic or atherosclerotic tissue to blood. In this regard, the sleeve provides biological protection.

**[0044]** Metal stents are known to sometimes physically damage tissue upon expansion. A sleeve made of a biological material is naturally soft by comparison to the metals or polymers used to construct stents. A sleeve comprised of collagen may be made sufficiently thick and durable so that it will prevent or at a minimum reduce any damage caused by the struts or other elements of any of the metal stents to the remaining healthy endothelium and the internal elastic lamina. The porosity of the sleeve may permit diffusion of essential fluid components from the blood to the surviving tissue below. In this regard, the benefit of the biological tissue protection by the sleeve and the physical protection provided are additive.

**[0045]** Both the biological and physical advantages as described herein can not be provided by synthetic sleeves as Dacron or PTFE.

**[0046]** In the case of variable diameter stents, the sleeve being somewhat elastic will fit the constricted stent and stretch with it upon deployment or it may be relatively loose fitting to accommodate the expanded stent upon deployment without any additional stress. Alternatively and most preferably, the stent may be expanded temporarily and the collagen placed thereon. The collagen may then be hydrated and the stent contracted to its unexpanded configuration. Then the collagen is dehydrated and it fits tightly to the stent.

**[0047]** A sleeve or a liner may be made to be more elastic by altering the crosslink density of the collagen. This can be accomplished in a variety of ways. Collagen sleeves may be prepared to have a very low crosslink density. The crosslink density may be increased in a variety of ways, dehydration, radiation exposure or heating are some examples of ways. Chemical agents which react with the collagen, such as short chain dialdehydes or formaldehyde may be employed to crosslink the collagen. The avoidance of the aforementioned processes can assure a non-crosslinked structure and result in somewhat elastic material. Crosslinking with the appropriate reagents can also enhance the elasticity of the collagen sleeve. Such reagents are the long chain difunctional molecules C12 and higher such as polyether or aliphatic dialdehydes, activated diesters such as N-hydroxy succinimide esters and diacid chlorides. These

active esters will react with amines present on the collagen chains thus bridging them by a flexible link which allows expansion without failure and tearing. Also, with amine functionality protected as an amide, the inter-chain, irreversible amide formation, which results from dehydration, is prevented.

**[0048]** A variety of stent types may be used in the invention. Some examples are shown in Figures 3-6. In Figure 3 there is shown a braided self-expanding stent generally designated 40. As is clear from the Figure, stent 40 has a cylindrical configuration. The stent may be manufactured in a braiding machine, wherein the stainless steel monofilaments consist of a plurality of wires, each having a thickness of, for example, 0.08 mm. Figure 4 shows yet another stent configuration 50 which may be used in this invention. Other examples of this type of stent are disclosed in U.S. Patent 4,655,771; U.S. Patent 4,732,152; U.S. Patent 4,954,126 and U.S. Patent 5,061,275.

**[0049]** Referring now to Figures 5 and 6 an articulated stent 60 is shown with three stent segments 62 and two interconnecting hinge elements 64. Stent segments 62 are each made of individual wire elements welded together. Hinges 64 may be made of biocompatible spring material and may be of a smaller diameter than those used in forming stent segments 62. Hinges 64 are welded at each end to stent segments 62 using either laser or resistance welding techniques. Hinges 64 are preferably both attached to the same side of stent segments 62. Stent 60, shown in Figure 5, may be installed in an artery 66 with a sleeve 12 as shown in Figure 6 and may be bent as shown.

**[0050]** Other stent configurations and materials will be apparent to those familiar with this art.

**[0051]** Collagen sleeves may be made to cover both sides of the stent, inside and out so that its surfaces are entirely encompassed by collagen.

**[0052]** An example of one such embodiment is shown in Figure 7 which comprises a tubular stent generally indicated at 10 combined with an inner sleeve 13 of collagen material and an outer sleeve 12 of collagen material which provide in combination a stent/sleeve generally indicated at 15 for the purpose of vascular implantation. In some cases, it is preferred that the collagen sleeve 13 be joined to the interior surface of the stent by a suitable means such as collagen gel which acts as an adhesive, particularly when the stent is of the variable diameter type. Such gels are known in the art.

## EXAMPLE

**[0053]** Method for the preparation of the sleeve stent of Figure 7.

1. SIS sheet is stretched about 50% while allowed to air dry.
2. Dry SIS sheet is wrapped onto an inflated, standard angioplasty balloon, moistening along the seam

to ensure proper adhesion.

3. A tubular stent is then placed over the SIS.

4. A second sheet of SIS is wrapped over the exterior of the stent. This sheet may be wetted to facilitate handling. The SIS which resides inside the stent may be wetted with a small amount of distilled water immediately preceding this wrapping procedure also.

5. Open cell foam sheeting is then wrapped onto the outer second layer of collagen, followed by a wrap of dialysis tubing. This radial pressure insures continuous contact and adhesion between the collagen layers.

6. The entire construction is then immersed in water momentarily to wet the collagen.

7. The entire combination is then heated to about 40° - 70° C for about .5 - 3 hours, then cooled to room temperature. The purpose of this heat treatment is to bond the collagen layers together. It may optionally be accomplished by use of a chemical cross-linking agent.

8. The resultant device is liberated from the balloon after the dialysis tubing and foam are removed. Any excess collagen material is then trimmed from the ends of the covered stent.

[0054] A cast or molded version is shown being manufactured in Figure 8 which includes a cylindrical mold 80 into which a cylindrical stent 82 is placed on end. Preferably, mold 80 will be porous, such as a porous ceramic, so as to allow water to be drawn through the mold to facilitate set-up of the poured collagen. A collagen gel solution 83 is then poured into mold 80 around stent 82 and inside of stent 82 and allowed to set-up. Upon set-up, the stent embedded in collagen is removed from the mold and a longitudinal hole may be formed through the collagen inside the stent to provide a longitudinal opening therethrough. Otherwise, a mandrel or mold insert may be used for this purpose as well.

[0055] In other embodiments, the collagen material may be coated onto the stent surfaces as desired by spraying or dip coating or an electrophoretic technique or the like. The electrophoretic technique is a preferred coating technique and may be accomplished, for example, in a solution of acetic acid, acetone, water and collagen with a metal stent as the cathode, at a potential of about three volts. This process bears some resemblance to modern electroplating, where positively charged metal ions are reduced to their corresponding metal at the negatively charged cathode. In the case of collagen, the biomolecule is dissolved or suspended in an acidic solution. The acid imparts a positive charge to the protein, collagen, and allows it to travel in an electrical field. By attaching a metal object to the negative electrode of a power source, and then immersing both the positive and negative electrodes in the acidic collagen solution, a layer of collagen will form on the negatively charged surface. The result is a coated stent of

the type shown in Figures 19 and 20 which will preferably include openings in the coating coincident with the openings in the stent.

## 5 EXAMPLE

Collagen Coated Stent (Type IV) via Electrodeposition

### [0056]

A. A solution of Sigma type IV human collagen (50 mg) was placed in a polypropylene tube with 3 ml water, 1 ml of acetic acid and 2 ml of acetone. This mixture was homogenized to a viscous solution via high shear mixing for ca. 3 minutes. The solution was diluted with water, then filtered through a cotton plug. The solution was allowed to stand for 1 hour to eliminate air bubbles.

B. A cylindrical container was fashioned out of polypropylene and charged with 1 ml of the above prepared solution A. To this container was added a nitinol substrate attached to the negative lead of a variable voltage power supply which was set at 3 volts. The positive electrode was furnished with a 0.010 inch diameter wire which was placed ca. 4 mm from the substrate. The power supply was turned on and gas evolution was immediately evident on the surfaces of each electrode. This was maintained for several minutes, then the electrodes were removed from the collagen solution. An even gelatinous mass was evident on the substrate, which contained several bubbles. Upon standing for 1 to 2 minutes, the bubbles were gone, and the electrodes were once again placed in the bath. After three additional minutes of treatment, the substrate was withdrawn from the bath and allowed to dry. The coating appeared to be continuous via visual inspection.

[0057] Another coating technique is shown in U.S. Patent 5,275,826.

[0058] Referring now to Figure 9, a tubular metal stent generally indicated at 10 carries within it a cylindrical liner or inner sleeve of collagen material generally indicated at 12 to provide a combination stent/liner generally indicated at 14 for the purpose of vascular implantation.

[0059] Stent 10, as already described hereinabove, is of any type, typically a metal such as for example stainless steel, nitinol, superelastic alloys and other metals or a suitable polymer or any other suitable material and may be of a fixed diameter or of a variable diameter, the latter being more preferred and well known in the art.

[0060] Collagen liner 12 as described hereinbefore, may be of collagen per se or it may be applied directly to the stent or it may be carried as 12c on a support 12d as shown in Figure 10 for application to a stent.

[0061] When the collagen liner is comprised of two dif-

ferent materials which are joined together as shown in Figure 10, it may be referred to as a bilayer structure. When placed in a stent, layer 12c is placed luminally with layer 12d contacting the inner surface of the stent. Layer 12d, which may be in contact with the vessel wall through openings in the stent in such an arrangement, is preferably strong and enables the inner luminal layer 12c itself to have the structural integrity necessary to ensure ease of loading, delivery and deployment. Layer 12c may for example be comprised of a collagenous material in the range of 5 to 200 microns thick. Such a biologically derived material may be harvested from a donor source, cleaned of unwanted tissues and formed into the tube by wrapping it around a mandrel and bonding the material to itself. Synthetic materials may be used to comprise the support of layer 12d of the liner, however, vascular graft materials such as PTFE, woven dacron, polyurethane and the like may also be used. Resorbable polymers (PLLA, PGA, PDLLA, PHB, polyanhydrides) are another choice for the support layer 12d of the liner 12. These materials may be formed into a tube by extrusion, solvent casting, injection molding, etc. or spinning into fibers and weaving into a tubular structure. A tube of one of the aforementioned polymers may also be constructed by a non-woven fiber technique.

**[0062]** The innermost or luminal side, *i.e.*, layer 12c of the liner serves a different function than the support layer 12d. The luminal surface or layer 12c must be a substrate for the growth of endothelial cells, as well as a reservoir for therapeutic agents. Preferred material is fibular Type I collagen and/or porcine Type IV collagen in the range of 5-200 microns thick, although fibrin may also be used for this purpose. Highly hydrated materials, such as cross linked hydrogels meet the drug holding requirement for the luminal portion of the liner, examples of which are polyethers, polyalcohols, polypyrrolidones, polypeptides, polyacids and the like. The layer 12 may also be a mixture of the above materials with a drug binding, ionic or covalent, molecule. One such molecule would be protamine, which effectively ionically binds heparin. These polymers can also be treated with growth factors, such as RGD peptides to promote endothelialization. The preferred method of drug incorporation would involve the preparation of a solution of the therapeutic agent and allowing the dehydrated luminal side of the sleeve to swell with the solution. Upon evaporation of the carrier solvent, the drug would be made to reside in the matrix which comprises the inner layer of the liner, *i.e.*, layer 12c. The device may act as a sponge to soak-up a drug in solution and to elute it from the stent upon implantation.

**[0063]** The term "collagen" or "collagen material" should also be understood to include the material referred to as Small Intestine Submucosa (SIS) which has particular use in this invention, alone and in combination with other collagen material such as Type I. SIS is comprised of a bilayer structure in which one layer is pre-

dominantly (stratum compactum) Type IV and the second layer is a mixture of Type I (muscularis mucosa) and Type III material. It is described in detail in U.S. Patents 4,902,508; 4,956,178 and 5,281,422. The luminal side of the SIS as used in preferred embodiments of this invention are predominantly a Type IV collagen material.

**[0064]** As with other collagen material, SIS may be used herein with or without a support layer such as a layer 12d as shown in Figure 10. It may also be used as the support layer 12c in combination with a layer 12d of Type I collagen as shown in Figure 10. SIS functions well without a support layer because it is itself a multi-layer structure.

**[0065]** In yet another embodiment, a SIS layer may be combined with a Type I layer to provide a one-way flow structure with reservoir arrangement as shown schematically in Figure 11. In this arrangement, a cylindrical wire mesh stent 10 carries a tubular bilayer liner generally indicated at 12 comprised of two layers 12c and 12d. Layer 12c contacts the inner surface of stent 10 and is a Type I collagen material and may carry a drug or the like, acting as a reservoir. Luminal layer 12d is SIS material and inherently functions to allow flow of drug from layer 12c into the luminal interior of the stent through the liminal layer 12d of stent 10 but does not permit appreciable fluid flow into layer 12c from the interior of the stent.

**[0066]** Variations of this Figure 11 arrangement are shown in Figures 12 and 13. In Figure 12, stent 10 carries an inner or luminal liner made up of layers 12c and 12d as described for Figure 11 and an outer layer of the same combination to allow predominantly one-way flow of drug to the luminal interior of the stent and to the surface against which the stent rests when implanted.

**[0067]** In Figure 13, stent 10 carries an exterior layer 12 of unsupported SIS material and an inner liner comprised of layers 12c and 12d as in Figures 11 and 12. Layer 12c is Type I material acting as a drug reservoir as previously shown in Figures 11 and 12. Layer 12d is of SIS acting as the one-way flow-through for drugs and the like from layer 12c, as before.

**[0068]** As pointed out hereinabove, cells of the blood vessel wall synthesize and secrete several kinds of macromolecules forming extracellular matrix. Each of these macromolecules may be combined in a multitude of combinations to form composites. Such materials as already pointed out, are referred to herein generally as "collagen".

**[0069]** A primary result of the use of a collagen liner made of natural components is that cellular regrowth of endothelium will take place onto a natural surface that is essentially undamaged and uniform. In this regard, the liner provides biological protection.

**[0070]** The liner may be tightly fitted to the stent in much the same way as described hereinabove with reference to the outer sleeve arrangement.

**[0071]** The liner may be attached to the stent in a wide variety of ways. The basic goal of attachment in the pre-

ferred form is to provide a stent device in which the supporting stent framework is substantially, if not completely, isolated from the blood flow by the liner. This can be achieved by placing liner 12 in the inside dimension of the stent 10 and cuffing the ends of the liner over the ends of the stent as shown at 16 in Figure 14. This is an especially preferred arrangement. Cuffs 16 may either be under or over the outer sleeve. Cuffs 16 may be sutured to the stent, sutured from one cuff to the other, or otherwise bonded to the stent or to the liner itself. The collagen material may be welded, by the application of localized heat and pressure, or the application of a concentrated solution of collagen material which acts like glue.

**[0072]** The liner may also be attached to the stent by the use of pledgets (not shown). The pledget (or small swatch of material) can be placed on the outside of the stent. The liner, which resides on the luminal or inner surface of the stent, may be bonded to the pledget in a variety of ways. Among these are suturing, gluing and heat welding. In the case of a combination of liner with outer sleeve, these means of attachment may be used as well.

**[0073]** The liner may be placed in the stent via several methods. The stent may be made porous or perforated, thus allowing the liner material to act as a forming mandrel for a collagen sleeve. The collagen may also be precipitated onto the stent. This method would require the stent to be heated in a solution of collagen. The collagen forms a matrix on the surface of the stent, then when properly annealed, the collagen assumes a fibular, well organized structure conducive for the attachment and growth of cells.

**[0074]** A technique is indicated in Figure 15 in which the collagen 12 is cast inside the stent 10 in a manner similar to that described in connection with Figure 8. Upon set-up, the stent with a liner of cast collagen is removed from the mold and a hole may be formed through the collagen to provide a longitudinal opening there-through. Otherwise, a mandrel or mold insert (not shown) may be used for this purpose also. Holes may also be formed through the stent walls in the collagen if the stent is perforated or the like.

**[0075]** The liner may be attached to the stent by any of several design features which may be incorporated into the stent. By providing the stent with hooks, or other similar topography (not shown), the sleeve may be readily attached to the stent. The sleeve material may be impaled on such barbs, thus securing the sleeve. With hooks of the appropriate size, the collagen material may not be perforated, but rather embedded in the holding topography.

**[0076]** As can be seen from the foregoing, the invention provides in one embodiment a stent in which collagen liner material is placed within and/or on the outside of the stent thereby reducing thrombus formation and therapeutically treating the vessel when a suitable agent is included in the collagen.

**[0077]** It is to be understood that the collagen material referred to herein as layers may be in the form of sheets associated with the stent or deposited thereon, i.e., as a coating.

**[0078]** Thus, the collagen material may be coated onto the stent surfaces as desired by spraying or dip coating or electrodeposition or the like or attached in other ways as described above. Such a coating might be about 1-50 microns thick. A coated stent is shown in Figure 19, which will preferably be perforate as shown.

**[0079]** A collagen coated stent may also have a collagen sleeve over the collagen coating or under the collagen coating. For example, one may place a stent into a collagen sleeve, as shown in Figure 1, with an interference fit. The inside of the stent may then be coated with collagen so that the stent and interior of the sleeve are covered and bonded together. Preferably, in such an arrangement, the sleeve will be SIS and the coating Type I or Type IV. It is also possible in the case of an open-work stent such as shown in Figure 1 or 3, to coat the stent struts with collagen, place a collagen sleeve either over or inside the stent, or both, and then heat bond the sleeve and/or liner to the coating. This would preferably be done with Type IV collagen, especially SIS or with fibrin.

**[0080]** In some applications it may be desirable to include perforations in the collagen for fluid movement through the stent\collagen wall. Such an arrangement is readily obtained as stents are generally open or perforate with respect to their structure and perforations may be readily formed in a collagen liner, the perforations extending through the stent openings. Perforation in collagen liners of about 10-60 microns in diameter have been found satisfactory. The distribution of the perforations may be such as to be evenly spaced, such as at 30-60 micron spacing and to occupy about one-half of the liner surface areas. This, of course, may vary.

**[0081]** Lastly, there is a preferred orientation for placing collagen on the stent when the collagen is used in the form of a sheet which is wrapped around the stent or a tube inserted in the stent. It has been discovered that sheet collagen has the ability to stretch but that its stretchability is predominantly unidirectional. That is, most of the stretch is exhibited in one primary direction in a sheet. This is shown schematically by the parallel arrows 100 in Figure 16 for a sheet of collagen 110 which typically shows little or no stretch in a direction normal to the arrows.

**[0082]** It has been discovered that the collagen sheet, when used as a sleeve or liner on a stent which undergoes expansion and/or contraction, can be better accommodated if the collagen sheet is associated with the stent on a "bias". This will be more fully explained by reference to Figures 17 and 18. If a piece of collagen sheet 110a is taken from sheet 110 in the orientations shown in Figure 17, it can be seen that the stretch direction indicated by the arrows 100 is on a bias with respect to sheet 110a. In this case, the bias is 45° relative



to the edges of sheet 110a. If sheet 110a is oriented normally with respect to a stent 120 as shown in Figure 18, i.e., the edges of sheet 110a are normal to the longitudinal dimension of stent 120, when sheet 110a is wrapped around stent 120 to form a sleeve or rolled up (in direction shown at 112 in Figure 18) into a tube for insertion into stent 120 as a liner, the stretch properties of sheet 110a will be on a bias with respect to the longitudinal dimension of stent 120, in this case the bias is 45°, which is a preferred bias. Other degrees of bias are acceptable but 45° is preferred.

**[0083]** It can be seen from the foregoing that due to the variable dimensions in both diameter and length which occurs with stents, such an arrangement better accommodates collagen sleeves and liners to dimensional changes in both directions without disruption at seams and without tears in the material.

**[0084]** One preferred type of stent for use in this invention is one of the type disclosed in related application 08/246,320, filed May 19, 1994.

**[0085]** Figures 19 and 20 show a coated stent generally indicated at 140, the collagen coating 142 being best seen in Figure 20. Coating 142 is shown on both the inside and outside surfaces of the stent although it may be on either as well.

**[0086]** The above Examples and disclosure are intended to be illustrative and not exhaustive. These examples and description will suggest many variations and alternatives to one of ordinary skill in this art. Those familiar with the art may recognize other equivalents to the specific embodiments described herein which equivalents are also intended to be encompassed by the claims attached hereto.

## Claims

1. A vascular prosthesis comprised of a support framework (10,40,50,60,120,140) and a collagen material (12,110) overlying at least a portion of a surface thereof, with the collagen material being selected from supported and unsupported bovine or porcine collagen, laminin, keratin, glycosaminoglycans, proteoglycans, pure carbohydrates, fibrin, fibronectin, albumin, globulins, and other bloodborne proteins, hyaluronic acid or the like, combinations thereof and any natural materials that form membranes with collagen, the support framework comprising an expandable stent having a collapsed cylindrical position and an expanded cylindrical position, wherein the collagen material is in sheet form and is oriented with respect to the longitudinal dimension of the stent such that the stretch properties of the collagen are at an angle with respect to the longitudinal dimension of the stent.
2. The prosthesis of claim 1 wherein the framework is a stent of variable diameter.

3. The prosthesis according to any one of the previous claims wherein the stent is of the self-expanding type.
4. The prosthesis according to any one of the previous claims wherein the stent is coated with a collagen material.
5. The prosthesis according to any one of claims 1 to 3 wherein the stent is embedded in collagen material.
6. The prosthesis according to any one of claims 1 to 3 wherein the stent is comprised of an open framework including a collagen coating over the framework.
7. The prosthesis according to any one of claims 1 to 3 wherein the framework is comprised of a network of interconnecting struts coated with collagen.
8. The prosthesis according to any one of claims 1 to 3 wherein the framework is comprised of a wire network, the wire being coated with collagen.
9. The prosthesis according to any one of claims 1 to 3 wherein the stent is comprised of a generally cylindrical body coated with a collagen material and the collagen material is in the form of a sleeve overlying the stent.
10. The prosthesis of claim 9 wherein the collagen coating is Type IV and/or Type I and the collagen sleeve is comprised of Type IV.
11. The prosthesis according to any one of the previous claims wherein the collagen material forms a layer, the layer of collagen material being substantially the same length and substantially overlapping the stent.
12. The prosthesis according to any one of claims 1 to 8 in which the collagen material is in the form of a sleeve overlying the stent.
13. The prosthesis according to any one of claims 1 to 8 wherein the collagen material covers the stent inside and out.
14. The prosthesis according to any one of claims 1 to 8 wherein the collagen material is in the form of an outer sleeve and an inner sleeve.
15. The prosthesis according to any one of the previous claims wherein the collagen material is comprised of collagen per se.
16. The prosthesis according to any one of the previous

claims wherein the collagen material is comprised of collagen on a support.

17. The prosthesis of claim 16 wherein the support is a fabric.
18. The prosthesis according to any one of claims 9, 10, 12 or 14, wherein the sleeve has elastic properties.
19. The prosthesis according to any one of claims 9, 10, 12, 14 or 18, wherein the sleeve is sized large with respect to the framework at least before implantation.
20. The prosthesis according to any one of claims 1-8, wherein the collagen material is in the form of an inner luminal liner.
21. The prosthesis according to claim 20 wherein the collagen material comprises a bilayer arrangement.
22. The prosthesis according to claim 21 wherein one of the layers in the bilayer is a polymeric material.
23. The prosthesis according to any one of claims 20 to 22 wherein the liner has cuffs at either end which overlap the ends of the stent.
24. The prosthesis according to any one of claims 20 to 23 wherein the stent has wall openings and the liner is perforated.
25. The prosthesis of claim 24 wherein the perforations are about 10-60 microns in diameter.
26. The prosthesis according to any one of claims 21 to 25 wherein the bilayer liner is comprised of at least two types of collagen material.
27. The prosthesis according to any one of claims 21 to 26 wherein the collagen material includes Type I and Type IV layers.
28. The prosthesis of claim 27, wherein the Type IV is the innermost layer and the Type I layer includes a drug.
29. The prosthesis according to any one of claims 1 to 8 wherein the collagen material is a multi-layer arrangement of Type I and Type IV collagen on the outside of the stent.
30. The prosthesis of claim 29 wherein the Type IV is the outermost layer.
31. The prosthesis according to any one of claims 10 and 27-30 wherein the Type IV is SIS.

32. The prosthesis according to any one of claims 1 to 8 wherein the collagen material includes SIS on the outside of the stent.

- 5 33. The prosthesis according to any one of claims 1 to 8 wherein the collagen material is in the form of an inner and outer layer of SIS collagen positioned on the stent.
- 10 34. The prosthesis according to any one of claims 1 to 3 wherein the support framework is coated with a collagen material and the collagen material is in the form of a sleeve thereover.
- 15 35. The prosthesis of claim 34 wherein the sleeve is SIS and the coating is Type I or Type IV.
36. The prosthesis according to any one of the previous claims wherein the collagen includes added agent.
- 20 37. The prosthesis of claim 36 wherein the agent is heparin.

#### 25 Patentansprüche

1. Gefäßprothese, enthaltend ein Stützgerüst (10, 40, 50, 60, 120, 140) und ein wenigstens einen Teil von dessen Oberfläche bedeckendes Kollagenmaterial (12, 110), wobei das Kollagenmaterial ausgewählt ist aus geträgertem und ungeträgertem Rinder- oder Schweinekollagen, Laminin, Keratin, Glucosaminoglycane, Proteoglycane, reine Kohlenhydrate, Fibrin, Fibronectin, Albumin, Globuline, sowie andere aus Blut stammende Proteine, Hyaluronsäure oder dergleichen, Kombinationen davon, sowie beliebige natürliche Materialien die mit Kollagen Membranen bilden, wobei das Stützgerüst einen expandierbaren Stent umfasst, der eine kollabierte zylindrische Stellung und eine expandierte zylindrische Stellung aufweist, wobei das Kollagenmaterial in Blattform vorliegt und bezüglich der Längsausrichtung des Stent so orientiert ist, dass die Dehnungseigenschaften des Kollagen um einen Winkel bezüglich der Längsausdehnung des Stent ausgerichtet sind.
2. Prothese nach Anspruch 1, wobei das Gerüst ein Stent mit variablem Durchmesser ist.
3. Prothese nach einem der vorhergehenden Ansprüche, wobei der Stent selbstexpandierender Art ist.
4. Prothese nach einem der vorhergehenden Ansprüche, wobei der Stent mit einem Kollagenmaterial beschichtet ist.
5. Prothese nach einem der Ansprüche 1 bis 3, wobei

- der Stent in Kollagenmaterial eingebettet ist.
6. Prothese nach einem der Ansprüche 1 bis 3, wobei der Stent ein offenes Gerüst mit einer Kollagenbeschichtung auf dem Gerüst enthält. 5
  7. Prothese nach einem der Ansprüche 1 bis 3, wobei das Gerüst aus einem Geflecht von miteinander verbundenen und mit Kollagen beschichteten Streben besteht. 10
  8. Prothese nach einem der Ansprüche 1 bis 3, wobei das Gerüst aus einem Drahtgeflecht besteht, und der Draht mit Kollagen beschichtet ist. 15
  9. Prothese nach einem der Ansprüche 1 bis 3, wobei der Stent aus einem im allgemeinen zylindrischen Körper besteht, der mit einem Kollagenmaterial beschichtet ist, und das Kollagenmaterial in Form einer den Stent bedeckenden Hülle vorliegt. 20
  10. Prothese nach Anspruch 9, wobei die Kollagenbeschichtung vom Typ IV und/oder Type I ist und die Kollagenhülle aus Typ IV besteht. 25
  11. Prothese nach einem der vorhergehenden Ansprüche, wobei das Kollagenmaterial eine Schicht bildet, und die Schicht aus Kollagenmaterial im wesentlichen die gleiche Länge wie der Stent aufweist und diesen im wesentlichen überlappt. 30
  12. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial in Form einer den Stent bedeckenden Hülle vorliegt. 35
  13. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial den Stent innen und außen bedeckt.
  14. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial in Form einer äußeren Hülle und einer inneren Hülle vorliegt. 40
  15. Prothese nach einem der vorhergehenden Ansprüche, wobei das Kollagenmaterial aus Kollagen per se besteht. 45
  16. Prothese nach einem der vorhergehenden Ansprüche, wobei das Kollagenmaterial aus Kollagen auf einem Träger besteht. 50
  17. Prothese nach Anspruch 16, wobei der Träger ein Gewebe ist.
  18. Prothese nach einem der Ansprüche 9, 10, 12 oder 14, wobei die Hülle elastische Eigenschaften aufweist. 55
  19. Prothese nach einem der Ansprüche 9, 10, 12, 14 oder 18, wobei die Hülle zumindest vor der Implantation bezüglich des Gerüsts groß dimensioniert ist.
  20. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial in Form eines inneren luminalen Einsatzes vorliegt.
  21. Prothese nach Anspruch 20, wobei das Kollagenmaterial einen zweischichtigen Aufbau umfasst.
  22. Prothese nach Anspruch 21, wobei eine der Schichten in der Doppelschicht ein Polymermaterial ist.
  23. Prothese nach einem der Ansprüche 20 bis 22, wobei der Einsatz an jedem Ende Stulpen aufweist, welche die Enden des Stent überlappen.
  24. Prothese nach einem der Ansprüche 20 bis 23, wobei der Stent Wandöffnungen aufweist und der Einsatz perforiert ist.
  25. Prothese nach Anspruch 24, wobei die Perforationen etwa 10 bis 60 Mikron im Durchmesser aufweisen.
  26. Prothese nach einem der Ansprüche 21 bis 25, wobei der zweischichtige Einsatz aus mindestens zwei Arten von Kollagenmaterial besteht.
  27. Prothese nach einem der Ansprüche 21 bis 26, wobei das Kollagenmaterial Typ I und Typ IV Schichten umfasst.
  28. Prothese nach Anspruch 27, wobei die Typ IV die innerste Schicht ist, und die Typ I Schicht einen Wirkstoff umfasst.
  29. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial ein vielschichtiger Aufbau aus Typ I und Typ IV Kollagen auf der Außenseite des Stent ist.
  30. Prothese nach Anspruch 29, wobei Typ IV die äußerste Schicht ist.
  31. Prothese nach einem der Ansprüche 10 und 27 bis 30, wobei Typ IV SIS entspricht.
  32. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial SIS auf der Außenseite des Stent umfasst.
  33. Prothese nach einem der Ansprüche 1 bis 8, wobei das Kollagenmaterial in Form einer inneren und äußeren Schicht von SIS Kollagen vorliegt, das auf dem Stent positioniert ist.

34. Prothese nach einem der Ansprüche 1 bis 3, wobei das Stützgerüst mit einem Kollagenmaterial beschichtet ist und ein Kollagenmaterial in Form einer darüber liegenden Hülle vorliegt.
35. Prothese nach Anspruch 34, wobei die Hülle aus SIS besteht und die Beschichtung aus Typ I oder Typ IV ist.
36. Prothese nach einem der vorhergehenden Ansprüche, wobei das Kollagen einen zugesetzten Wirkstoff umfasst.
37. Prothese nach Anspruch 36, wobei der Wirkstoff Heparin ist.

#### Revendications

1. Prothèse vasculaire composée d'une structure (« framework ») de support (10, 40, 50, 60, 120, 140) et d'un matériau de collagène (12, 110) recouvrant au moins une partie de surface de celle-ci, avec le matériau de collagène étant choisi parmi l'acide hyaluronique ou semblable, la lamine, la kératine, les glycosaminoglycanes, les protéoglycanes, les carbohydrates purs, la fibrine, la fibronectine, l'albumine, les globulines, et d'autres protéines issues du sang, le collagène porcin ou bovin supporté ou non-supporté, les combinaisons de ceux-ci et tout matériau naturel qui forme les membranes présentant du collagène, la structure de support comprenant un élément tubulaire (« stent ») que l'on peut dilater présentant une position cylindrique fléchie et une position cylindrique dilatée, dans laquelle le matériau de collagène se présente sous la forme d'une feuille et est orienté en respectant la dimension longitudinale de l'élément tubulaire tel que les propriétés élastiques du collagène forment un angle en respectant la dimension longitudinale de l'élément tubulaire.
2. Prothèse selon la revendication 1 dans laquelle la structure est un élément de diamètre variable.
3. Prothèse selon l'une quelconque des revendications précédentes dans laquelle l'élément tubulaire est du type autodéployable.
4. Prothèse selon l'une quelconque des revendications précédentes dans laquelle l'élément tubulaire est revêtu d'un matériau de collagène.
5. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle l'élément tubulaire est enrobé dans un matériau de collagène.
6. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle l'élément tubulaire est composé d'une structure ouverte incluant un revêtement de collagène sur la structure.
7. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle la structure est composée d'un réseau de branches (« struts ») interconnectées revêtu de collagène.
8. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle la structure est composée d'un réseau de grille, la grille étant recouverte de collagène.
9. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle l'élément tubulaire est généralement composé d'un corps cylindrique revêtu d'un matériau de collagène et le matériau de collagène est sous la forme d'un manchon recouvrant l'élément tubulaire.
10. Prothèse selon la revendication 9 dans laquelle le revêtement de collagène est du Type IV et/ou de Type I et le manchon est composé de Type IV.
11. Prothèse selon l'une quelconque des revendications précédentes dans laquelle le matériau de collagène forme une couche, la couche de matériau de collagène étant sensiblement de la même longueur et recouvre sensiblement l'élément tubulaire.
12. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène est sous la forme d'un manchon recouvrant l'élément tubulaire.
13. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène couvre l'intérieur et l'extérieur de l'élément tubulaire.
14. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène est sous la forme d'un manchon externe et d'un manchon interne.
15. Prothèse selon l'une quelconque des revendications précédentes dans laquelle le matériau de collagène est composé de collagène per se.
16. Prothèse selon l'une quelconque des revendications précédentes dans laquelle le matériau de collagène est composé de collagène sur un support.
17. Prothèse selon la revendication 16 dans laquelle le support est un tissu (« fabric »).
18. Prothèse selon l'une quelconque des revendica-

tions 9, 10, 12 ou 14 dans laquelle le manchon présente des propriétés élastiques.

19. Prothèse selon l'une quelconque des revendications 9, 10, 12, 14 ou 18 dans laquelle le manchon est de taille large en respectant le support au moins avant l'implantation.

20. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène se présente sous la forme d'un liner interne comportant des lumières (« luminal liner »).

21. Prothèse selon la revendication 20 dans laquelle le matériau de collagène comprend une configuration bi-couche.

22. Prothèse selon la revendication 21 dans laquelle l'une des couches de la bi-couche est un matériau polymère.

23. Prothèse selon l'une quelconque des revendications 20 à 22 dans laquelle le liner présente des rebords (« cuffs ») à chaque extrémité qui recouvrent les extrémités de l'élément tubulaire.

24. Prothèse selon l'une quelconque des revendications 20 à 23 dans laquelle l'élément tubulaire présente des ouvertures de paroi et l'élément tubulaire est perforé.

25. Prothèse selon la revendication 24 dans laquelle les perforations sont d'environ 10-60 microns de diamètre.

26. Prothèse selon l'une quelconque des revendications 21 à 25 dans laquelle le liner bi-couche est composé d'au moins deux types de matériaux de collagène.

27. Prothèse selon l'une quelconque des revendications 21 à 26 dans laquelle le matériau de collagène inclut des couches de Type I et de Type IV.

28. Prothèse selon la revendication 27 dans laquelle le Type IV est la couche la plus interne et le Type IV contient un médicament.

29. Prothèse selon la revendication selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène est un collagène de configuration multi-couches de Type I et de Type IV à l'extérieur de l'élément tubulaire.

30. Prothèse selon la revendication 29 dans laquelle le Type IV est la couche la plus externe.

31. Prothèse selon l'une quelconque des revendica-

tions 10 et 27-30 dans laquelle la couche de Type IV est une SIS (« Small Intestine Submucosa », Sous-muqueuse de l'intestin grêle).

32. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène contient une SIS à l'extérieur de l'élément tubulaire.

33. Prothèse selon l'une quelconque des revendications 1 à 8 dans laquelle le matériau de collagène est sous la forme d'une couche interne et externe de collagène de SIS situé sur l'élément tubulaire.


34. Prothèse selon l'une quelconque des revendications 1 à 3 dans laquelle la structure de support est revêtue d'un matériau de collagène et le matériau de collagène est sous la forme d'un manchon recouvrant ce support.

35. Prothèse selon la revendication 34 dans lequel le manchon est une SIS et le revêtement est du Type I ou du Type IV.


36. Prothèse selon l'une quelconque des revendications précédentes dans laquelle le collagène contient un agent supplémentaire.

37. Prothèse selon la revendication 36 dans laquelle l'agent est l'héparine.


**Fig. 1**






**Fig. 2**




**Fig. 3**






**Fig. 7**




**Fig. 8**







*Fig. 9*




*Fig. 10*




**Fig. 11**




**Fig. 12**



**Fig. 13**



**Fig. 14**



**Fig. 15**




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20

